



EURO INDUSTRY COMPANY LIMITED

Performance Parameters --- LAMINATED GLASS AND TEMPERED GLASS

Item		Quality Requirements				
		Laminated Glass		Tempered Glass		
Thickness Tolerance (mm)	Thickness (mm)	Tolerance		Tolerance		
	2.7	2.55-2.85mm				
	3	2.70-3.00mm		2.70-3.00mm		
	3.2	3.05-3.35mm		3.05-3.35mm		
	4	3.80-4.20mm		3.80-4.20mm		
	5	4.70-5.00mm		4.70-5.00mm		
	6	5.80-6.20mm		5.80-6.20mm		
	8-12	±0.30mm		±0.30mm		
	15-19	±0.40mm		±0.40mm		
Edge Thickness (mm)	2.7-6	100mm: 0.06mm (Max)				
	8-12	100mm: 0.10mm (Max)				
Cross Bow (mm)	2.7-6	≤ 1.00mm/m		≤ 2.00mm/m		
	8-12	≤ 1.50mm/m		≤ 2.00mm/m		
	15-19			≤ 2.00mm/m		
Edge Quality (mm)	2.7-6	Flake	≤ 3mm		≤ 3mm	
		Flare/Bevel	≤ 3mm		≤ 3mm	
		Corners	≤ 4mm		≤ 4mm	
	8-12	Flake	≤ 6mm		≤ 6mm	
		Flare/Bevel	≤ 4mm		≤ 6mm	
		Corners	≤ 6mm		≤ 10mm	
	15-19	Flake			≤ 12mm	
		Flare/Bevel			≤ 12mm	
		Corners			≤ 25mm	
Over Score & Cutter Drag		Not Allowed		Not Allowed		
Size Tolerance (mm)	Thickness (mm)	≤ 2000	> 2000	≤ 2000	> 2000	
	2.7-6	±2mm	±3mm	±2mm	±3mm	
	8-12	±3mm	±4mm	±4mm	±4mm	
	15-19		±6mm	±6mm	±6mm	
Squareness	For all thickness	Diagonal measurement difference/2 ≤ 0.2% the diagonal length				
Linear Flaws	Scratch, Roll Scuff,	No flaws visible at 2 meters when		No flaws visible at 1 meter when		
Bloom	For all thickness			≤ Grade 2.0		
Non-Continuous Defects	Defect size (d)	Not allowed per square meter		Not allowed per square meter		
	d ≤ 1.0mm	Allowed		Allowed		
	1.0 < d ≤	1		1		
	d > 1.5mm	None		None		
Optical Destortion		Zebra ≥ 45°		Zebra ≥ 45°		